

CHEMISOL ZINC 98% SPRAY

CHEMISOL Zinc 98% Spray is an anti-corrosive with high density and large covering capacity.



- ✓ **Fast-drying**
- ✓ **Good filling properties**
- ✓ **Exceptional corrosion prevention**
- ✓ **Resistant to fuels, chemicals and weather influences**
- ✓ **Welding permitted**
- ✓ **Excellent adhesion and coverage**

APPLICATIONS

Recommended for galvanized and untreated steel. For metal surfaces protection against corrosion.

INDICATIONS

The surface must be clean, dry and degreased.

Remove old and loose varnish, rust and sand the surface.

The spray must be at room temperature. The best temperature of use is between 15°C and 25°C. Before use, shake the spray can for 2 minutes and spray a sample. The distance to the surface to be treated should be approximately 25 to 30 centimetres.

INSTRUCTIONS

Apply CHEMISOL Zinc 98% Spray in several thin layers, and wait at least 5 minutes between each one. Before applying the next layer, shake the spray can again. When desired, after the zinc spray is dry, you can use a varnish layer.

After use, clean the valve (turn the can upside down and press the nozzle for approximately 5 seconds until only gas comes out).

The drying time depends on the room temperature, air humidity and thickness of the product applied.

TECHNICAL SPECIFICATIONS

Base	Epoxy ester
EU-VOC solvent percentage	≈ 54% w/w
Solid content	≈ 46% w/w
Coverage	1,25 to 1,75 m ²
Drying	After 10 to 15 minutes
Touch	After 20 to 30 minutes
Hardening	After 24 hours
Temperature resistance	Up to 350°C

These values may vary depending on environmental factors such as temperature and humidity. The curing time is higher the lower the temperature and humidity and the greater the thickness of the product.

SAP	ml	Shelf life			EAN
CHC070102	400	10 years	Grey	6	5604630051996

Note: The technical information provided, either verbally or in writing, is based on our current knowledge and should be considered as collaboration without commitment. The use of the product is beyond our control, thus, we rule out any responsibility for its improper use. The customer is responsible to confirm and validate (by testing) if the product is suitable for the process and the type of use in question. Our purpose is exclusively to guarantee the quality of the products, according to our standards.