

CHEMISOL ZINC SPRAY

CHEMISOL Zinc Spray is a high-quality zinc repair spray for repairing minor damage in galvanized steel surfaces through dipping.



- ✓ **Fast-drying**
- ✓ **Good filling properties**
- ✓ **Exceptional corrosion prevention**
- ✓ **Resistant to fuels, chemicals and weather influences**
- ✓ **Welding permitted**
- ✓ **Excellent adhesion and coverage**

APPLICATIONS

Recommended for use on doors, pipe connections, wood and wire fences, gutters, drain pipes, guard rails and containers.

INDICATIONS

The surface should be clean, dry and degreased.

Remove old and loose varnish, rust and sand the surface.

The spray must be at room temperature. The best temperature of use is between 15°C and 25°C. Before use, shake the spray can for 2 minutes and spray a sample.

The distance to the surface to be treated should be approximately 25 to 30 centimetres.

INSTRUCTIONS

Apply CHEMISOL Zinc Spray in several thin layers, and wait at least 5 minutes between each one. Before applying the next layer, shake the spray can again. When desired, after the zinc spray is dry, apply a varnish layer.

After use, clean the valve (turn the can upside down and press the nozzle for approximately 5 seconds until only gas comes out).

The drying time depends on the room temperature, air humidity and thickness of the product applied.



TECHNICAL SPECIFICATIONS

Base	Acrylic resin
EU-VOC solvent percentage	≈ 93% w/w
Solid substances percentage	≈ 7%
Yield	0,75 g/seconds
Coverage	1,25 to 1,75 m ²
Drying	Between 5 and 10 minutes
Touch	Between 10 and 20 minutes
Hardening	After 2 hours
Temperature resistance	Up to 110°C

These values may vary depending on environmental factors such as temperature and humidity. The curing time is higher the lower the temperature and humidity and the greater the thickness of the product.

SAP	ml	Validade			EAN
CHC070103	400	10 years	Silver	6	5604630052009

Note: The technical information provided, either verbally or in writing, is based on our current knowledge and should be considered as collaboration without commitment. The use of the product is beyond our control, thus, we rule out any responsibility for its improper use. The customer is responsible to confirm and validate (by testing) if the product is suitable for the process and the type of use in question. Our purpose is exclusively to guarantee the quality of the products, according to our standards.